

31-Aug-09

Sample	Current (mA)	% Power	Height (cm)	Sputter Time (sec)	Zygo Thickness Result (nm)			Avg	St. Dev	Dep rate (nm/sec)
					1	2	3			
1	18	25%	10.5	200	10	6	14	10	4	0.05
2	18	25%	10.5	400	16	16	19	17	2	0.04
3	18	25%	10.5	600	21	17	22	20	3	0.03
4	18	25%	10.5	800	48	44	43	45	3	0.06

